

# Technisches Datenblatt

Perfekt rübergebracht auf

BERBERICH  
PAPIER

Niveus® SUPERIOR

Kopier / Laser Papier



**Hauptsorte:** Kopier / Laser Papier

**Stoffklasse:** holzfrei

**Oberfläche:** matt

**Zertifizierung:** FSC® C018175 Mix Credit (ab Lager), EU-Ecolabel, ColorLok®, Cradle to Cradle Certified®

**mit Laser- und Inkjet-Garantie**



## Technische Richtlinien für Niveus® SUPERIOR:

Eigenschaft/Einheit	60 ±2.5	70 ±2.5	80 ±3.0	90 ±3.5	100 ±4.0	120 ±4.0	160 ±6.0	200 ±6.0	250 ±6.0	Prüfmethode
Flächengewicht, g/m <sup>2</sup>	60 ±2.5	70 ±2.5	80 ±3.0	90 ±3.5	100 ±4.0	120 ±4.0	160 ±6.0	200 ±6.0	250 ±6.0	ISO 536
Dicke, µm	85 ±4	96 ±3	107 ±3	119 ±3	131 ±4	153 ±4	202 ±5	252 ±6	315 ±7	ISO 534
Rauigkeit Bendtsen, ml/min	200 ±50	150 ±50	150 ±50	150 ±50	150 ±50	150 ±50	150 ±50	150 ±50	150 ±50	ISO 8791-2
Opazität, %	87.0 ±1	91.0 ±1	94.0 ±1	95.0 ±1	96.0 ±1	97.5 ±1	99.0 ±1	100.0	100.0	ISO 2471
Absolute Feuchte, %	4.6 ±6	4.6 ±6	5.0 ±5	5.0 ±5	5.0 ±5	5.0 ±5	5.0 ±5	5.5 ±6	5.5 ±6	ISO 287
Weisse m. UV, %	114.0 ±2.0	114.0 ±2.0	114.0 ±2.0	114.0 ±2.0	114.0 ±2.0	114.0 ±2.0	114.0 ±2.0	114.0 ±2.0	114.0 ±2.0	ISO 2470
CIE Weisse, %	170 ±4.0	170 ±4.0	170 ±4.0	170 ±4.0	170 ±4.0	170 ±4.0	170 ±4.0	170 ±4.0	170 ±4.0	ISO 11475

Product meets EN 12281, requirements for copy paper for dry toner imaging processes and ISO 9706, requirements for permanence for paper. Production processes certified according to ISO 9001, ISO 14001 and OHSAS 18001. Standard measurement uncertainty between laboratories is not incorporated.

This specification is valid for one year after issue or good till cancelled.